

Oily paint MA-15

Specification

- It protects coated surface from external impact
- It has an attractive decorative appearance



Sphere of application

It is intended for interior and exterior finishing works (excluding floor painting) and for painting metal and wood surfaces.

Technical data

Consumption standard of 1 layer	140-240 g/m ² , depending on the type of surface and way of application.
Solvent	solvent TM DekART, 10% maximum of the total paint weight.
Application	Apply with a brush or a roller.
Drying period (23 °C, 50% RH)	24 hours. Drying period increases if the temperature is getting down and relative air humidity is getting higher."
Solids content (DSTU ISO 3251)	88-90 %
Density (DSTU ISO 2811-1)	about 1,5 g/cm ³
Hardness (DSTU ISO 1522)	about 12 sec., Konig pendulum.
Warranty period	12 months from the date of manufacturing.
Packaging	1 kg, 2,5 kg, 60 kg
Color	white, green, bright blue.
Gloss	semigloss.

Composition

Dry oil, pigments, extenders, solvent, additives.



Application instruction

1 Surface preparation

The surface shall be dry and cleaned from dirt, grease, dust, Clean thoroughly the surface from old loose coatings (loose paint and varnish) in mechanical (a scraper, a wire brush), thermal (hot air fan, infrared radiation) or chemical way (paint removal solutions). Defected surfaces (holes, rends, cracks) shall be filled with Putty for wood TM Farbex. Puttied surfaces shall be sandpapered with small-grained paper till smooth, then remove the dust.

2 Priming

Previously coated wooden surfaces do not require undercoating.

Previously uncoated or unputtied wooden surfaces shall be primed with Alkyd wood protective primer TM "Delfi". Be sure that the surface is completely dry before priming.

Previously uncoated metal surfaces shall be primed with Alkyd primer GF-021 TM "DekArt"

Previously uncoated concrete surfaces shall be primed with a solution of paint and solvent at a rate of 1:1.

3 Application

Make sure that the surface is dry before coating. The paint shall be thoroughly stirred till homogeneous conditions. The paint is ready to use. It is recommended to use the product of one batch applying the finishing layer on the surface to avoid deviation in color shades. If you use products of different batches it is necessary to mix them. The paint shall be applied evenly in 1-2 thin layers. Each next layer shall be applied in 24 hours. Application is performed at the temperature from + 10°C till + 35 °C and relative air humidity no more than 80%. After the coating is applied it shall not be affected by atmospheric precipitation before finishing coating for 24 hours. The final hardening of the surface and the acquisition of its properties occurs 14 days after the coating.

4 Tool cleaning

Clean tools with a solvent and then with warm water with detergents if necessary.

SAFETY

Keep away from fire! Keep in tightly closed original containers at the temperature from -20 °C till + 40 °C. Keep out of moisture, direct sunlight and food. Keep in the places out of reach of children. During application use personal safety gear (work clothes, rubber gloves, a respirator and safety glasses). Provide well-arranged ventilation of the space if the application is indoors and 48 hours after coating. If skin contact, wash thoroughly with water and soap. If eye contact, rinse with plenty of running water. Consult a doctor if necessary. VOC content: cat. A/d (SB): < 300 g/l. Actual VOC content ≤ 200 g/l. It doesn't contain lead and lead compounds. More detailed information you can read in the safety data sheet. The product has a sanitary-epidemical conclusion of the state expertise.

ENVIRONMENTAL PROTECTION

Do not empty into drains, ponds and in soil ! Liquid rests shall be delivered to the waste drop-off point. Rests of dry products and empty containers shall be recycled as common construction waste, in accordance with the Law.

The authenticity of this information is based on laboratory tests and practical knowledge. The quality of the product completely corresponds to the demands of TU U 20.3-32318370-016:2015. As a manufacturer, the company isn't responsible for the damage caused by application, which is not in accordance with the directions. The applicability of the product for specific purposes shall be defined entirely by the consumer. Current information loses validity with the issue of a new edition.

