

High-quality WB acrylic facade paint "Facade"

Specification

It creates hard, longlasting, resistant to aggressive effects of nature (precipitation, UV radiation, moisture, alkali, temperature fluctuation) high-quality matt coating with high vapor permeability and low water absorption. It is easy to apply. It doesn't run when applying.



Sphere of application

It is intended for coating of facades of the buildings with mineral surfaces (mortar, chalky mortar plasters, filler, brick, concrete, slag block) as well as gypsum and wooden surfaces. It is recommended for the primary and renewal coating of the facades of living, historical, public, administrative, and office buildings, warehouses, and architectural monuments, and for works in seaside districts.

Technical data

Consumption standard of 1 layer	115-140 g/m ² , depending on the way of application and type of surface.
Thinner	Water. It is allowed diluting maximum 10 % of the total weight of the product
Application	It is applied with a roller, a brush or a spray gun.
Drying period (23 °C, 50% RH)	max. 1 hour. Drying period increases if the temperature falls and the relative air humidity raises and depends on the consumption of the paint (thickness of the coat).
Color base	A, B, C, TR. It is shaded according to NCS color range.
Solids content (DSTU ISO 3251)	60±2 % (base A), 55±2 % (base B, C, TR)
Density (DSTU ISO 2811-1)	≈ 1,52 g/cm ³ (base A), ≈ 1,43 g/cm ³ (base B), 1,36 – 1,39 g/cm ³ (base C, TR)
Gloss (DSTU ISO 2813)	max. 5 GU at 85° (matt, G ₃ , SSU EN 1062-1)
Dry film thickness	50-100 microns, (E ₂ , SSU EN 1062-1)
Particle size	max. 30 microns, (Fine grained, S ₁ , SSU EN 1062-1:2012)
Vapor permeability (EN ISO 7783-2)	more than 150 g/(m ² *day), (high, V1, DSTU EN 1062-1)
Water permeability (DSTU EN 1062-3)	less than 0,5 kg/(m ² *hour 0,5), (medium, W2, DSTU EN 1062-1)
Marking acc. to the DSTU EN 1062-1	G ₃ E ₁ S ₁ V ₁ W ₂ A ₄ C ₀
Warranty period	24 months from the date of manufacture (at the temperature from +5 °C till +35 °C)
Packaging	Base A - 1,4 kg, 4,2 kg, 7 kg, 14 kg Base B, C, TR - 1,2 kg, 3,6 kg, 6 kg, 12 kg
Color	base B, base C, base TR, white (base A).

Composition

Acrylic dispersion, pigments, water, extenders, additives.



Tinting

The product is manufactured in following bases:

Base A. It is intended for use as a white finishing coating or for tinting in pastel, light colors.

Base B. It is intended for tinting in colors of medium saturation.

Base C. It is intended for tinting in saturated colors.

Base TR. It is intended for tinting in bright and dark colors.

Base B, C, and TR cannot be used without tinting.

It is tinted manually using pigment concentrate Farbex Color, other water-based tinting pastes, or with tinting machines according to the color catalog NCS and others. If you tint with other products, tinting machines, or catalogs, you must take into account their suitability for exterior works, silicone products, and carry out test tinting and application.

For saturated colors (yellow, black, pink, orange, green, or bright green), the base surface must be of one color. Otherwise, you might apply additional coats. To lessen the consumption of saturated color paint, the surface must be previously painted with base A (white or tinted in a similar pastel color paint).

We recommend using the product of the same batch (the paint and the colorant) for coating the surfaces to avoid differences in color shades. Use the same batch for the surfaces that join. In case you use the product of different batches, it is necessary to mix them. Carry out a test application on a small area to check that the color corresponds to the chosen one. We do not recommend diluting the product for a finish coating. After tinting, insignificant deviations of product technical data are possible.

A hint: When you choose a color, take into account the lighting in the premises and location of façade elements according to the sun and their structure. Elements in shadow, inclined surfaces, elements with different roughness, and daylight period will provide a different perception of the same color.

Application instruction

The condition for receiving a desired result is following directions for using the paint product and preparing the surface.

1 Preliminary preparation

The surface is prepared according to DSTU-N B A.3.1-23:2013 and DSTU-N B B.2.6-212:2016.

The surface must be dry – the humidity of the surface on all stages of preparation and paint works must be less than 5% for cement and cement-sand surfaces and less than 1% for gypsum ones.

The surface must be clean from chalk and lime whitewashings, grease and oily stains, and other contaminations, efflorescence, dust (including abrasive dust after polishing plasters and stuccos), old paint products and wallpapers (which stick to the surface not secure), polymer adhesives, and runs of construction mortars or composites.

Mineral surfaces must be hard, without fragile parts or edges. The base materials like plaster, stucco, insulating or adhesive elements must be completely dry and be ready for priming and coating with acrylic water-based products.

Parts of the surface infected with mould or fungi must be removed: first mechanically and then treated with antiseptic for mineral surfaces TM Farbex.

Remove contaminations, infections, old coatings, or fragile parts with a wire brush, a spatula, a scratcher or with a polisher.

Correct appeared defects with Plaster TM Farbex (depending on the character of the defects).

Existing metal elements in the base surface or those that will be used after painting must be made of galvanized or stainless steel. When you use iron elements, they must be initially protected against corrosion with special primers or other products.

Check the compatibility of the products on a small area following technical recommendations or specialists' consultation before you use other products (an adhesive, an antiseptic, a plaster, etc.).

Follow the directions precisely (especially drying period and subsequent treatment) when further priming and painting construction mortars or products. For example, fresh cement plasters must not be treated for 28 days, fresh concrete - 3 months, the surfaces of insulating systems - 7 days.

2 Priming

Providing maximum exploitation resistance and better decorative effect, depending on the type of surface, it must be primed:

Wooden porous surfaces – with acrylic wood-protective primer TM Maxima. Attention! The primer raises the wood fibers, which is why the surface must be polished before applying the paint.

Mineral surfaces – with acrylic deep-penetrating primer TM Farbex.

Take into account recommendations about priming construction mortars or products. If necessary, call the specialists of POLYSAN.

3 Application

Before applying the paint, make sure that the surface is dry enough after preparation. The paint is ready to use. Stir the paint thoroughly before use. Filter it and dilute with water if necessary. Abnormal dilution spoils the quality of the coating! Apply the paint in 1-2 coats. Apply a subsequent coat when the previous one is fully dry, but not before 2 hours. Very porous, rough, or highly contrasted surfaces demand more coats of the paint and consumption. The precise consumption is determined by a test application on a small area on the surface.

We recommend continuously applying in one direction with the same consumption. Carry out the application "from edge to edge (from



corner to corner)" or within the limits of the decorative element without breaks. When you carry out an application on a large area and/or during a long period, we recommend stirring the paint from time to time. We do not recommend keeping the container with the paint open for a long period. Carry out the application at the temperature of the air and the surface from + 5 °C until +35 °C and relative air humidity less than 80 %. Do not apply the paint under direct sunlight, strong wind, frost and precipitation. After application, the coating shall not be affected by precipitation or subzero temperatures for 12 hours. The coating obtains complete hardness and resistance to mechanical load after 28 days.

High-quality façade paint “Façade” can be applied by following methods:

Method of application	Quantity of diluent	Jet size	Pressure
Airless spraying	0 – 10 %	0.019" - 0.023"	15 - 18 MPa (≈ 150 - 180 bar)
Pneumatic spraying	0 – 10 %	2,0 – 2,5 mm	0,4 – 0,5 MPa (≈ 4-5 bar)
A brush / a roller	0 – 5 %	-	-

The tools must be recommended for water-based products.

When you apply with a roller, we recommend using a cuvette for homogeneous wetting the tool. Attention! For a smoother coating, we recommend using a roller with a short nap.

When you apply with by a spraying method, follow the instructions for exploitation. Airless spraying is more preferable. The reason is that when you use pneumatic spraying, you have to dilute the product, and often diluting can be on the maximum recommended limit, which can occur, lessening the thickness of the coating and creating runs.

For a quality coating, you must obtain painting skills, especially if you use a professional instrument.

During façade works, we recommend using façade tents and scaffolding.

Compatibility with other coatings

Depending on the exploitation conditions, it can be used with different primers and finishing coatings. The examples are stated further. Call the specialists of POLYSAN to receive more detailed recommendations.

Previous coating – acrylic water-based products.

Subsequent coating – acrylic water-based products.

Compatibility of products is recommended for testing on a small area of the surface.

4

Tool cleaning

Clean tools with water after application. Do not let them dry. The dry product shall be removed from the tools in a mechanical way.

SAFETY

Do not mix with other products and (or) organic solvents! Keep in tightly closed original containers at the temperature from +5 °C till +35 °C. Keep out of moisture, direct sunlight, frost and out of reach of children. During application use personal safety gear (work clothes, rubber gloves, a respirator and safety glasses). If application is indoors well-arranged ventilation shall be provided. If skin contact, wash thoroughly with water and soap. If eye contact, rinse with plenty of running water. Consult a doctor if necessary. VOC content: cat. A/c (WB): < 40 g/l. Actual VOC content ≤ 20 g/l. More detailed information you can read in the safety data sheet. The product has a sanitary-epidemical conclusion of the state expertise.

ENVIRONMENTAL PROTECTION

Do not empty into drains, ponds and in soil! Liquid rests shall be delivered to the waste drop-off point. Rests of dry products and empty containers shall be recycled as common construction waste, in accordance with the Law.

The authenticity of this information is based on laboratory tests and practical knowledge. The quality of the product completely corresponds to the demands of DSTU EN 13300: 2012, DSTU EN 1062-1:2012 and TU U 24.3-32318370-009:2011. As a manufacturer, the company isn't responsible for the damage caused by application, which is not in accordance with the directions. Applicability of the product for specific purposes shall be defined entirely by the consumer. Current information loses validity with the issue of a new edition.

