

Acrylic pannel varnish



Specification

- It is intended for indoor and outdoor works.
- It creates solid and elastic film, which does not grow yellow and does not decrepitate with time.
- It does not change the colour of the wood and emphasizes its natural beaty.
- It is resistant to washing with cleaning agents.
- It has high adhesion to the basis.
- It dries quickly.





Sphere of application

Acrylic panel varnish is intended for decorative and protective treatment of linings, scrub-boards, window frames, panels of natural wood, plywood, chip board, MDF, mineral surfaces (bricks, decorative stone, concrete, plaster, putty). **Do not use for lacquering of floor and furniture!**



Technical data

Consumption standard of 1 layer	80-100 g/m², depending on the kind of wood and quality of timber as well as way of application.
Thinner	Water. Delution of the product is possible but maximum 10% of the total weight.
Application	It is applied with a roller, a brush or a spraying gun.
Drying period (23 °C, 50% RH)	< 2 hour. Drying period increases if the temperature is getting down and relative air humidity is increasing.
Gloss (DSTU ISO 2813)	Glossy. Minimal 60 GU at 60° Silky-matt. Maximal 20 GU at 60°
Hardness (DSTU ISO 1522)	> 25 sec, Konig pendulum
Solids content (DSTU ISO 3251)	30±2 %
Density (DSTU ISO 2811-1)	1,02 - 1,05 g/cm³, depending on the gloss degree.
VOC content (ISO 11890)	< 25 g/l
Warranty period	36 months from the date of manufacturing (at the temperature from +5 $^{\circ}$ C till +35 $^{\circ}$ C)
Packaging	0,9 kg, 3 kg, 5 kg, 10 kg
Color	colorless.
Gloss	glossy, silky matt.



Composition

Acrylic dispersion, water, additives.

Application instruction

1

Surface preparation

-

Priming

7

Applying of finishing layer

Make sure that the undercoated cover is dry enough before applying the finish coating.

The varnish is ready for use, if needed dilute it with water.

The recommended application of the product is 2 layers with intermediate polishing. The next layer shall be applied not earlier, than in 2-3 hours. The final hardening of the surface and the acquisition of its properties occurs 14 days after the coating.









Application is performed at the temperature from + 10 °C till + 30 °C and relative air humidity no more than 80%.

Tool cleaning

Clean tools with water after application. Do not let them dry. Dry product shall be removed from the tools in mechanical way.



SAFETY

Do not mix with other products and (or) organic solvents! Keep in tightly closed original containers at the temperature from +5 °C till +35 °C. Keep out of moisture, direct sunlight, frost and out of reach of children. During application use personal safety gear (work clothes, rubber gloves, a respirator and safety glasses). If application is indoors well-arranged ventilation shall be provided. If skin contact, wash thoroughly with water and soap. If eye contact, rinse with plenty of running water. Consult a doctor if necessary. VOC content: cat. A/e (WB): <130 g/l. Actual VOC content ≤ 25 g/l. More detailed information you can read from the safety data sheet. The product has a sanitary-epidemical conclusion of the state expertise.



ENVIRONMENTAL PROTECTION

Do not empty into drains, ponds and in soil! Liquid rests shall be delivered to the waste drop-off point. Rests of dry products and empty containers shall be recycled as common construction waste, in accordance with the Law.

The authenticity of this information is based on laboratory tests and practical knowledge. The quality of the product completely corresponds to the demands of TU U 24.3-32318370-009:2011. As a manufacturer, the company isn't responsible for the damage caused by application, which is not in accordance with the directions. The applicability of the product for specific purposes shall be defined entirely by the consumer. Current information loses validity with the issue of a new edition.



