

Acrylic yacht varnish

Specification

It has high resistance to weather effects: UV radiation, lasting influence of fresh and salt water, and also to the influence of humidity and household cleaning agents. It has increased wear resistance, resistance to scratching, impact and other intensive mechanical loadings. It creates solid and elastic film, which does not deprecitate with time. It also creates glassy cover, which emphasizes wood structure.



Sphere of application

It is intended for lasting protection and giving decorative effect to wooden above water parts and interior parts of sea and river ships as well as for window frames, doors and other wooden surfaces. For indoor and outdoor use.

Technical data

Consumption standard of 1 layer	80-100 ml/m ² , depending on the kind of wood and quality of timber as well as way of application.
Thinner	Water. Delution of the product is possible but maximum 10% of the total weight.
Application	It is applied with a roller, a brush or a spraying gun.
Drying period (23 °C, 50% RH)	4 hour. Drying period increases if the temperature is getting down and relative air humidity is increasing. Maximum hardness and wear resistance of the coating is achieved after 14 days.
Gloss (DSTU ISO 2813)	Minimal 60 GU at 60°
Hardness (DSTU ISO 1522)	> 80 sec, Konig pendulum
Solids content (DSTU ISO 3251)	21±2 %
Density (DSTU ISO 2811-1)	≈ 1,03 g/cm ³
VOC content (ISO 11890)	< 100 g/l
Warranty period	24 months from the date of manufacturing (at the temperature from +5 °C till +35 °C)
Packaging	0,75 l, 2,5 l, 5 l, 20 l
Color	colorless.
Gloss	glossy.

Composition

Polyurethane-acrylic dispersion, water, additives.

Application instruction

1 Surface preparation

The surface shall be dry (maximum humidity is 20%). Clean thoroughly the surface of oils, wax, mud, grease, dust, blue stain, decay, old paint coats and other dirt till clean wood.

Clean dirty areas with a dry brush.

Mould and plants shall be removed manually (with a scraper or a wire brush). Then treat the surface with Antiseptic for wooden surfaces TM Farbex.

Remove resin at the places of knots in mechanical way.

To receive a smooth surface without visible places of old coatings (paint or varnish), it shall be totally removed from the surface in mechanical (with a scratcher, a floor scrubber), thermal (a hot dryer, infra-red rays) or chemical way (paint removing treatments).

It is not recommended to clean the surface by methods, which can damage wood fibers (for example, sandblast apparatus).

Defected surfaces (holes, rends, cracks) shall be filled with Putty for wood TM Farbex.

Polish the surface and remove the dust.



2 Priming

Make sure that wooden surface is clean and dry before priming.

It is recommended to prime new or cleaned from old rests surfaces with Wood protective acrylic primer TM Maxima for providing the best defensive effect.

Edges of wooden products shall be treated more carefully and completely impregnated.

3 Applying of finishing layer

Make sure that the primed cover is dry enough before applying the finish coating.

The varnish is ready for use, if needed dilute it with water. Stir the varnish before application.

The recommended application of the product is 2-3 coats with intermediate polishing. The next coat shall be applied not earlier, than in 4 hours. The final hardening of the surface and the acquisition of its properties occurs 14 days after the coating.

Application is performed at the temperature from + 10 °C till + 30 °C and relative air humidity no more than 80%.

Do not apply the varnish under direct sunlight, strong wind, frost and atmospheric precipitation. After the coating is applied it shall not be affected by atmospheric precipitation and sub-zero temperatures for 24 hours.

4 Tool cleaning

Clean tools with water after application. Do not let them dry. Dry product shall be removed from the tools in mechanical way.

SAFETY

Do not mix with other products and (or) organic solvents! Keep in tightly closed original containers at the temperature from +5 °C till +35 °C. Keep out of moisture, direct sunlight, frost and out of reach of children. During application use personal safety gear (work clothes, rubber gloves, a respirator and safety glasses). If application is indoors well-arranged ventilation shall be provided. If skin contact, wash thoroughly with water and soap. If eye contact, rinse with plenty of running water. Consult a doctor if necessary. Actual VOC content ≤ 100 g/l (not subject to TR). More detailed information you can read from the safety data sheet. The product has a sanitary-epidemical conclusion of the state expertise.

ENVIRONMENTAL PROTECTION

Do not empty into drains, ponds and in soil ! Liquid rests shall be delivered to the waste drop-off point. Rests of dry products and empty containers shall be recycled as common construction waste, in accordance with the Law.

The authenticity of this information is based on laboratory tests and practical knowledge. The quality of the product completely corresponds to the demands of TU U 24.3-32318370-009:2011. As a manufacturer, the company isn't responsible for the damage caused by application, which is not in accordance with the directions. The applicability of the product for specific purposes shall be defined entirely by the consumer. Current information loses validity with the issue of a new edition.

